


12/19 Beckman Coulter N4 Plus / N5 Run Data							Angle: 90	Repetitions: 6	Sample ID: Cannasol Labs NS-500													
Size (nm)	Volume %	Volume %	Volume %	Volume %	Volume %	Volume %	AVG Vol %	AVG Size	Bin Width	Bin Height	Normalized Bin Height	Cumulative Percent	Dv90 Identify	Dv90 slope	Dv90 y-int	Dv90 calc	Size (nm)	Cumulative Percent	u100 identify	u100 slope	u100 y-int	u100 calc
1	0	0	0	0	0	0	0.00	0.00	unk	0.00	0.00	0.00	0	0.000	0	0	1	0.00	0	0.0000	0.000	0.000
1.25893	0	0	0	0	0	0	0.00	0.00	0.29	0.00	0.00	0.00	0	0.000	0	0	1.25893	0.00	0	0.0000	0.000	0.000
1.58489	0	0	0	0	0	0	0.00	0.00	0.37	0.00	0.00	0.00	0	0.000	0	0	1.58489	0.00	0	0.0000	0.000	0.000
1.99526	0	0	0	0	0	0	0.00	0.00	0.46	0.00	0.00	0.00	0	0.000	0	0	1.99526	0.00	0	0.0000	0.000	0.000
2.51189	0	0	0	0	0	0	0.00	0.00	0.58	0.00	0.00	0.00	0	0.000	0	0	2.51189	0.00	0	0.0000	0.000	0.000
3.16228	0	0	0	0	0	0	0.00	0.00	0.73	0.00	0.00	0.00	0	0.000	0	0	3.16228	0.00	0	0.0000	0.000	0.000
3.98107	0	0	0	0	0	0	0.00	0.00	0.92	0.00	0.00	0.00	0	0.000	0	0	3.98107	0.00	0	0.0000	0.000	0.000
5.01187	0	0	0	0	0	0	0.00	0.00	1.16	0.00	0.00	0.00	0	0.000	0	0	5.01187	0.00	0	0.0000	0.000	0.000
6.30957	0	0	0	0	0	0	0.00	0.00	1.47	0.00	0.00	0.00	0	0.000	0	0	6.30957	0.00	0	0.0000	0.000	0.000
7.94328	0	0	0	0	0	0	0.00	0.00	1.85	0.00	0.00	0.00	0	0.000	0	0	7.94328	0.00	0	0.0000	0.000	0.000
10	0	0	0	23.4225	0	0	4.68	0.47	2.32	2.02	0.41	4.68	0	0.000	0	0	10	4.68	0	0.0000	0.000	0.000
12.5893	0	0	0	27.744	0	0	5.55	0.70	2.92	1.90	0.39	10.23	0	0.000	0	0	12.5893	10.23	0	0.0000	0.000	0.000
15.8489	0	0	0	8.86685	0	0	1.77	0.28	3.68	0.48	0.10	12.01	0	0.000	0	0	15.8489	12.01	0	0.0000	0.000	0.000
19.9526	21.1089	0	10.0136	0	3.85764	0	7.00	1.40	4.64	1.51	0.31	19.00	0	0.000	0	0	19.9526	19.00	0	0.0000	0.000	0.000
25.1189	25.5827	0	54.8456	0	62.4313	0	28.57	7.18	5.84	4.90	1.00	47.57	0	0.000	0	0	25.1189	47.57	0	0.0000	0.000	0.000
31.6228	16.9416	59.5797	15.9336	6.29662	16.0087	0	22.95	7.26	7.35	3.12	0.64	70.53	0	0.000	0	0	31.6228	70.53	0	0.0000	0.000	0.000
39.8107	9.76963	23.3019	0	11.8766	0	0	8.99	3.58	9.25	0.97	0.20	79.52	0	0.000	0	0	39.8107	79.52	0	0.0000	0.000	0.000
50.1187	8.16314	0	0	10.563	0	0	3.75	1.88	11.64	0.32	0.07	83.26	0	0.000	0	0	50.1187	83.26	0	0.0000	0.000	0.000
63.0957	8.33387	0	6.88671	6.08853	6.68051	0	5.60	3.53	14.66	0.38	0.08	88.86	1	0.472	59.057427	65.51045	63.0957	88.86	0	0.0000	0.000	0.000
79.4328	6.38513	8.44161	11.7434	3.00589	9.00651	0	7.72	6.13	18.45	0.42	0.09	96.58	0	0.000	0	0	79.4328	96.58	1	0.1523	84.479	99.708
100	3.01708	8.4999	0.577105	1.55193	2.01544	0	3.13	3.13	23.23	0.13	0.03	99.71	0	0.000	0	0	100	99.71	0	0.0000	0.000	0.000
125.893	0.697973	0.176931	0	0.584102	0	0	0.29	0.37	29.24	0.01	0.00	100.00	0	0.000	0	0	125.893	100.00	0	0.0000	0.000	0.000
158.489	0	0	0	0	0	0	0.00	0.00	36.82	0.00	0.00	100.00	0	0.000	0.000	0.000	158.489	100.00	0	0.0000	0.000	0.000
199.526	0	0	0	0	0	0	0.00	0.00	46.35	0.00	0.00	100.00	0	0.000	0	0	199.526	100.00	1	0.0000	0.000	0.000
251.189	0	0	0	0	0	0	0.00	0.00	58.35	0.00	0.00	100.00	0	0.000	0	0	251.189	100.00	1	0.0000	0.000	0.000
316.228	0	0	0	0	0	0	0.00	0.00	73.46	0.00	0.00	100.00	0	0.000	0	0	316.228	100.00	0	0.0000	0.000	0.000
398.107	0	0	0	0	0	0	0.00	0.00	92.48	0.00	0.00	100.00	0	0.000	0	0	398.107	100.00	0	0.0000	0.000	0.000
501.187	0	0	0	0	0	0	0.00	0.00	116.43	0.00	0.00	100.00	0	0.000	0	0	501.187	100.00	0	0.0000	0.000	0.000
630.957	0	0	0	0	0	0	0.00	0.00	146.57	0.00	0.00	100.00	0	0.000	0	0	630.957	100.00	0	0.0000	0.000	0.000
794.328	0	0	0	0	0	0	0.00	0.00	184.52	0.00	0.00	100.00	0	0.000	0	0	794.328	100.00	0	0.0000	0.000	0.000
1000	0	0	0	0	0	0	0.00	0.00	205.67	0.00	0.00	100.00	0	0.000	0	0	1000	100.00	0	0.0000	0.000	0.000

Processed SDP Volume Distribution



Volume-weighted Average Size 35.9 nm

Dv90: 65.5 nm

Percentage of Material Under 100 nm 99.7 %

Tested By:

Josh Doty